

# Product/Process Resistance Matrix

System:	NT01	NT02	NT03	NT04	NT05	NT06	NT11	NT14	NT15	NT19	NT20	NT21	NT23	NT23BR	NT24	NT25	NT27	NT28	NT29	NT30	NT33	
Process:	SFO	WHS	WNH	F/G	F/G	F/G	DO/LP	G	F/G	F/G	F/G	F/G	F/G	F/G	OG	F/G	SFO	SS	PP/SS	PP/SS	F/G/SS	
Property:																						
<b>Oil/Grease</b>	G	P	G	E	G	P	E	E	P	G	F	G	G	E	G	G	G	G	E	P	G	
<b>Water</b>	E	E	E	E	E	E	G	E	E	G	E	F	F	G	E	E	E	E	E	E	G	
<b>Chocolate</b>	E	F	E	E	F	P	E	E	P	G	F	G	E	E	G	E	G	G	E	P	G	
<b>Odor*</b>	High	Low	Med	Low	Low	Low	Low	Med	Low	Low	Low	Low	Low	Low	Med	Low	Med	Med	Med	Low	Low	
<b>Alcohol**</b>	G	G	G	F	F	P	G	E	P	P	F	P	F	F	G	G	G	P	E	P	P	
<b>Heat Resistance***</b>	G	G	G	E	G	P	G	G	P	G	G	G	G	G	G	G	G	G	G	P	G	
<b>Sterilization:</b>																						
<b>ETO</b>	E	E	E	E	E	E	E	E	E	E	E	G	G	G	E	E	E	E	E	E	E	
<b>Steam</b>	E	E	E	E	E	E	E	E	E	E	E	F-G	F-G	F-G	E	E	E	E	E	E	E	
<b>Gamma</b>	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	

\* Odor transmission potential

\*\* 10 wipes with an isopropyl alcohol saturated swab

\*\*\* Vehicle softening at 300F

Ratings: **E**: Excellent **G**: Good **F**: Fair **P**: Poor

**SFO**: Sheetfed Offset    **WHS**: Web-Heatset Offset    **WNH**: Web No-Heat    **F/G**: Flexographic/Gravure    **DO/LP**: Dry Offset/Letterpress  
**G**: Gravure    **OG**: Offset Gravure    **SS**: Silk Screen    **PP/SS**: Pad Print/Silk Screen    **F/G/SS**: Flexographic/Gravure/Silk Screen