



**SURETERIC<sup>®</sup>**  
AQUEOUS ENTERIC COATING SYSTEM

Technical Data Sheet  
Coating Applications

## Delayed Release Coating of Aspirin Granules with Sureteric<sup>®</sup>

### Purpose:

To evaluate Sureteric, as an aqueous, delayed release coating for granules in pilot and production scale fluid bed equipment.

### Methods:

Several trials have been conducted in both Glatt and Aeromatic fluid-bed equipment utilizing the Wurster process. Aspirin granules (40 mesh) were used as a substrate for all of the coating trials. In each case, a 1-2% weight gain of an Opadry<sup>®</sup> (YS-2-7013) as a subcoat was used prior to the Sureteric application. Typical coating conditions for the application of Sureteric are reported in Table 1 below:

**Table 1. Coating Conditions for the Application of Sureteric**

Specification	Glatt GPCC-3	Glatt GPCC-60 HS	Aero MP-2
Bed Charge	2-3.0kg	50.0kg	15.0kg
Sureteric % solids	15.0	15.0	15.0
% Weight gain applied	20.0	20.0	20.0
Spray nozzle	Schlick 1.2mm	Schlick "04"	Schlick 1.2mm
Plate	"C"	"B"	8%
Inlet air temp °C	60-65	65-75	65-70
Exhaust air temp °C	35-40	30-35	30-35
Spray rate g/min	20-25	275-350	65-75

### Process Considerations:

In the Wurster process, the spray nozzle and a portion of the liquid feed line are placed in the supply plenum directly within the source of heated process air. Care must be taken not to stop the flow of Sureteric suspension without clearing the feed lines and nozzle. Typically, this can be accomplished by disconnecting the liquid feed line from the nozzle with the atomization air still turned on. This will allow any Sureteric remaining in the nozzle to be aspirated from the assembly by the atomizing air. If the Sureteric remains static in the nozzle under elevated temperature conditions, nozzle plugging may occur.

### Dissolution Results:


Coated granules were tested using U.S.P. Delayed Release Method I. Typically a 15-20% weight gain of Sureteric will provide enteric protection with < 10% aspirin release in 0.1N HCL over 2 hours and suitable drug release with greater than 80% release in less than 90 minutes in phosphate buffer, pH 6.8.

**Table 2. Drug Release from Aspirin in 0.1N HCL**

% Aspirin released after 2 hours in 0.1N HCL (Limit <10%)		
Glatt GPCG-3	Glatt GPCG-60 HS	Aero MP2
5.51	8.98	7.55



**Figure 1. Sureteric Coated Aspirin Granules: 20% Weight Gain.  
Dissolution in 6.8 Phosphate Buffer**



**Conclusion:**

Successful delayed release coating of aspirin granules with Sureteric in a Wurster process has been demonstrated from pilot through production scale.

**World Headquarters**

Colorcon

415 Moyer Blvd., P.O. Box 24, West Point, PA 19486-0024

Tel: 215-699-7733 Fax: 215-661-2605 Web Site @<http://www.colorcon.com> E.mail: [modified\\_release@colorcon.com](mailto:modified_release@colorcon.com)

<b>Locations</b>	<b>Telephone</b>	<b>Facsimile</b>	<b>Locations</b>	<b>Telephone</b>	<b>Facsimile</b>
<i>United States</i>			<i>Asia/Pacific</i>		
Santa Ana, California	714-549-0631	714-549-4921	Singapore	65-6438-0318	65-6438-0178
Indianapolis, Indiana	317-545-6211	317-545-6218	Nishiyama, Japan	81-5-4465-2711	81-5-4465-2730
Humacao, Puerto Rico	787-852-3815	787-852-0030	Shanghai, China	86-21-5442-2222	86-21-5442-2229
<i>Europe</i>			Goa, India	91-832-288-3434	91-832-288-3440
Dartford, Kent, England	44-1322-293000	44-1322-627200	Seoul, Korea	82-2-2057-2713	82-2-2057-2179
Bougival, France	33-1-3082-1582	33-1-3082-7879	<i>Latin America</i>		
Idstein, Germany	49-6126-9961-0	49-6126-9961-11	Buenos Aires, Argentina	54-911-4552-1565	54-911-4552-3997
Gallarate, Italy	39-0331-776932	39-0331-776831	Cotia, Brasil	55-11-4612-4262	55-11-4612-3307
Budapest, Hungary	36-1-200-8000	36-1-200-8010	Bogota, Colombia	571-418-1202	571-418-1257
Barcelona, Spain	34-9-3589-3756	34-9-3589-3792	Santa Fe, Mexico	525-5-3000-5700	525-5-3000-5701
Istanbul, Turkey	90-216-465-0360	90-216-465-0361	Caracas, Venezuela	58-212-442-4819	58-212-442-8724

The information contained herein, to the best of our knowledge is true and accurate. Any recommendations or suggestions are made without warranty or guarantee, since the conditions of use are beyond our control. Any information contained herein is intended as a recommendation for use of our products so as not to infringe on any patent.

© Colorcon, 2006. The information contained in this document is proprietary to Colorcon and may not be used or disseminated inappropriately. Sureteric® and Opadry® are registered trademarks of BPSI Holdings Inc. [mr/sureteric/granule\\_coating/06.2006](http://mr/sureteric/granule_coating/06.2006), Rev 3

First Published 02.1999. Revised 10.2006