

Coating Parameters

Opadry[®] fx[™], special effects film coatings, create visually unique tablets that impart color, gloss and a lustrous appearance. An endless variety of shades, hues, and gloss levels are achieved when using the system alone, or in combination with pigmented Opadry[®] II, high performance film coating systems. The parameters listed on the table below are based on coating trials with Opadry fx performed by Colorcon. Individual product and machine functions should be taken into account and conditions altered as required.

Pan Type		Fully Perforated Side Vented Coating Pan				Conventional Pan
Pan Diameter	cm	38.1	60.96	122	152.4	40.64
	in	15	24	48	60	16
Solution Preparation						
Solvent		Purified Water	Purified Water	Purified Water	Purified Water	Purified Water
Solids Content	% w/w	7.5	7.5	7.5	7.5	7.5
Run Objectives						
Theoretical Weight Gain	% w/w	1 - 3	1 - 3	1 - 3	1 - 3	1 - 3
Tablet Charge [†]	kg [†]	1.5 - 3.0	12 - 15	120 - 160	320 - 350	3
Gun Configuration						
Example Spray Gun	type	Schlick 931/7-1 S22	Spraying Systems 1/8 VAU	Schlick 931/7-1 S35 (ABC)	Manesty	Schlick 970/7-1 S75
Number of Guns	guns	1	1 - 2	3 - 4	5 - 6	1
Nozzle Diameter	mm	1.2	1.02	1.2	1.2	1.2
	in	0.05	0.04	0.05	0.05	0.05
Gun to Bed Distance	cm	10	17	25	25	15
	in	4	7	10	10	6
Gun to Gun Distance	cm	N/A	10	15	15	N/A
	in	N/A	4	6	6	N/A
Atomizing Air Pressure	bar	1.4	1.7	2.5	2.5	1.4
	psi	20	25	36	36	20
Pattern Air Pressure	bar	1.4	1.7	2.5	2.5	1.4
	psi	20	25	36	36	20
Process Parameters						
Drying Air Volume	cu.m/hr	250 - 290	424 - 470	2300 - 3060	5440 - 6630	140
	cu.ft/min	147 - 175	250 - 275	1350 - 1800	3200 - 3900	80
Pan Speed	rpm*	18	14	8	6	20
Pre-warm Tablet Bed	°C	45 - 50	45 - 50	45 - 50	45 - 50	45 - 50
	°F	113 - 122	113 - 122	113 - 122	113 - 122	113 - 122
Inlet Air Temperature	°C	60	65	65	65	65
	°F	140	149	149	149	149
Tablet Bed Temperature	°C	43 - 48	43 - 48	43 - 48	43 - 48	43 - 48
	°F	109 - 118	109 - 118	109 - 118	109 - 118	109 - 118
Spray Rate	g/min	15 - 18	40 - 60	260 - 430	650 - 750	12
Approximate Coating Times	min	15 - 60	30 - 100	45 - 150	55 - 190	31 - 100
<p>*Pan speed should be set so that even mixing of the bed occurs. This will be influenced by tablet size, shape, friability and baffle type in the pan.</p> <p>[†]Tablet charge is dependent on tablet size and shape.</p>						

For more information, contact your Colorcon representative or call:

North America
+1-215-699-7733

Europe/Middle East/Africa
+44-(0)-1322-293000

Asia Pacific
+65-6438-0318

Latin America
+54-11-4552-1565

You can also visit our website at www.colorcon.com



©BPSI Holdings LLC. 2009. The information contained in this document is proprietary to Colorcon and may not be used or disseminated inappropriately.

All trademarks, except where noted, are property of BPSI Holding LLC.