

Coating Parameters for the Use of Acryl-EZE® II -- Enteric Protection for Multiparticulates

Acryl-EZE II is a fully formulated, dry acrylic-enteric coating system, for the application of a delayed release film coating to solid dosage forms such as tablets, granules and beads. Combining the benefits of a fully formulated coating system with a globally accepted delayed release polymer (EUDRAGIT® L100-55*), Acryl-EZE II is readily dispersible in water for easy application. The coating system can be pigmented to meet marketing requirements and provides consistent, reproducible delayed release profiles.

The coating parameters which are recommended for use with Acryl-EZE II are based on Colorcon trial data. Individual product and machine functions should be taken into account and conditions altered as required. For further technical advice, please contact your Colorcon Technical Representative.

Coating Parameter	Glatt GPCG-1.1	Glatt GPCG-2	Glatt GPCG-3	Freund-Vector VFC-60M with Wurster Accelerator
Solvent	Distilled water	Distilled water	Distilled water	Distilled water
Solids content (% w/w)	20	20	20	20
Theoretical weight gain (%)	25	20-40	25	20-40
Substrate	SUGLETS®	Lansoprazole MP	SUGLETS®	Lansoprazole MP
Substrate mesh	30-35	18-20	30-35	18-20
Substrate charge (kg)	0.6	2	2.5	50
Inlet air temperature (°C)	55	55	45	65
Drying air volume (m³/hr)	70	130	130	1359
Product temperature (°C)	33	35	33	35
Exhaust air temperature (°C)	32	35	34	35
Spray equipment	Schlick 970	Schlick 970	Schlick 970	Schlick 0/4
Partition Height (cm)	2.0	1.8	1.8	4.6
Fluid nozzle (mm)	1.1	1.1	1.0	2.2
Air cap (mm)	2.0	2.0	2.0	9.0
Atomizing air pressure (bar)	1.8	2	2.5	3
Spray rate (g/min)	13	12-15	15	250

Acryl-EZE II is reconstituted to 20% w/w solids dispersion for use. Recommended weight gains of Acryl-EZE II start at 20% for enteric performance depending on the shape, size and surface area of the multiparticulate. A sub-coat may be required to separate strongly acidic or basic drugs from the enteric polymer or to strengthen the dosage form prior to enteric coating. A colored top-coat may be applied if required.

* Methacrylic acid copolymer type C

The information contained herein, to the best of Colorcon, Inc.'s knowledge is true and accurate. Any recommendations or suggestions of Colorcon, Inc. with regard to the products provided by Colorcon, Inc. are made without warranty, either implied or expressed, because of the variations in methods, conditions and equipment which may be used in commercially processing the products, and no such warranties are made for the suitability of the products for any applications that you may have disclosed. Colorcon, Inc. shall not be liable for loss of profit or for incidental, special or consequential loss or damages.

Colorcon, Inc. makes no warranty, either expressed or implied, that the use of the products provided by Colorcon, Inc., will not infringe any trademark, trade name, copyright, patent or other rights held by any third person or entity when used in the customer's application.

For more information, contact your Colorcon representative or call:

North America
+1-215-699-7733

Europe/Middle East/Africa
+44-(0)-1322-293000

Asia Pacific
+65-6438-0318

Latin America
+54-11-5556-7700

You can also visit our website at www.colorcon.com



© BPSI Holdings LLC, 2014.

The information contained in this document is proprietary to Colorcon and may not be used or disseminated inappropriately.

All trademarks, except where noted, are property of BPSI Holdings, LLC.

EUDRAGIT® is a trademark of Evonik Röhm GmbH, Darmstadt, Germany.

PI_acryl-eze_MP_coat_par_ver2_10_2015

This document is valid at the time of distribution. Distributed 30-May-2023 (UTC)