

Product/Process Resistance Matrix

NS06
(10/14)

System:	NT01	NT02	NT03	NT04	NT05	NT06	NT11	NT14	NT15	NT19	NT20	NT21	NT23	NT23BR	NT24	NT25	NT27	NT28	NT29	NT30	NT33	
Process:	SFO	WHS	WNH	F/G	F/G	F/G	DO/LP	G	F/G	F/G	F/G	F/G	F/G	F/G	OG	F/G	SFO	SS	PP/SS	PP/SS	F/G/SS	
Property:																						
Oil/Grease	G	P	G	E	G	P	E	E	P	G	F	G	G	E	G	G	G	G	E	P	G	
Water	E	E	E	E	E	E	G	E	E	G	E	F	F	G	E	E	E	E	E	E	G	
Chocolate	E	F	E	E	F	P	E	E	P	G	F	G	E	E	G	E	G	G	E	P	G	
Odor*	High	Low	Med	Low	Low	Low	Low	Med	Low	Low	Low	Low	Low	Low	Med	Low	Med	Med	Med	Low	Low	
Alcohol**	G	G	G	F	F	P	G	E	P	P	F	P	F	F	G	G	G	P	E	P	P	
Heat Resistance***	G	G	G	E	G	P	G	G	P	G	G	G	G	G	G	G	G	G	G	P	G	
Sterilization:																						
ETO	E	E	E	E	E	E	E	E	E	E	E	G	G	G	E	E	E	E	E	E	E	
Steam	E	E	E	E	E	E	E	E	E	E	E	F-G	F-G	F-G	E	E	E	E	E	E	E	
Gamma	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	

* Odor transmission potential

** 10 wipes with an isopropyl alcohol saturated swab

*** Vehicle softening at 300F

Ratings: **E**: Excellent **G**: Good **F**: Fair **P**: Poor

SFO: Sheetfed Offset **WHS**: Web-Heatset Offset **WNH**: Web No-Heat **F/G**: Flexographic/Gravure **DO/LP**: Dry Offset/Letterpress
G: Gravure **OG**: Offset Gravure **SS**: Silk Screen **PP/SS**: Pad Print/Silk Screen **F/G/SS**: Flexographic/Gravure/Silk Screen



For more information, contact your Colorcon representative or call 1-800-724-0624
You can also visit our website at <http://www.colorcon.com/notox>

©BPSI 2014Holdings LLC,

The information contained in this document is proprietary to Colorcon Inc. and may not be used or disseminated inappropriately
All trademarks, except where noted, are property of BPSI Holdings, LLC.

The information contained herein, to the best of Colorcon Inc.'s knowledge, is true and accurate. Any recommendations or suggestions of Colorcon Inc. with regard to the products provided by Colorcon Inc. are made without warranty, either implied or expressed, because of the variations in methods, conditions and equipment which may be used in commercially processing the products, and no such warranties are made for the suitability of the products for any applications that you may have disclosed. Colorcon Inc. shall not be liable for loss of profit or for incidental, special or consequential loss or damages. The information contained in this document is not intended as legal advice, and should not be relied upon for that purpose. Any regulatory information provided is intended solely as initial general guidance. Each customer is responsible for determining the regulatory acceptability of the use of the product in their specific application