

No-Tox[®] ALCOHOL-BASED INKS

(FLEXOGRAPHIC/GRAVURE)

-OR-

(PAD PRINT/SCREEN PRINT)

NT33
(12/14)

- Product Type:** Specially modified alcohol-soluble food grade polymer.
- Printing Methods:** Available for either flexographic/gravure presses and for pad print/screen print processes.
- General Directions:** An alcohol reducible ink for applications where ultra low toxicity is desirable. Depending on color, can be made completely food grade. Ideal for applications such as synthetic and natural meat casings, as well as for use on all paper stocks.
- Suggested Uses:** Synthetic and natural meat casings, labels, coupons, promotions and other in- package inserts where food grade or ultra low toxicity components are desired.
- Note:** Some colors may not be able to be provided in a completely food grade system. Also, some colors are not recommended for contact with aqueous and fatty foods because of poor water and bleed resistance properties. If use in contact with aqueous or fatty foods is anticipated, thorough end-use testing should be completed before use in production runs. For additional information contact our Technical Service Department.
- Stocks:** All types of FDA and USDA acceptable coated and uncoated paper stocks, vegetable parchment, glassine and many synthetic and natural meat casing materials.
- Plates and Rollers:** *Flexographic/Gravure* - all natural and synthetic rubber plates and rollers and photopolymer plates are acceptable.
Pad Print - compatible with all types of pad print equipment and elastomeric pads.
Silk Screen - all types of screens and squeegees are acceptable. Mesh size is dependent on print and end-use requirements.
- Color Availability:** Dependent upon specific application. Contact our Technical Services Department for assistance.
- Shelf Life:** Minimum one year in unopened containers.
- Additives and Diluents:** Normally supplied at higher than press ready viscosity to allow for dilution at press side.

Recommended Solvents: The following solvents and blends are intended only as a guide. Other diluents and/or ratios may be better suited for your application. For additional assistance, contact our Technical Services Department.

Flexographic/Gravure Diluents:

Fast:

70% Ethyl Alcohol
30% Ethyl Acetate

Normal:

100% Normal Propyl Alcohol

Slow:

70% Normal Propyl Alcohol
30% Glycol Ether*
*PM recommended

Pad Print/Screen Print Diluents:

Fast:

100% Normal Butyl Alcohol

Normal:

50% Normal Butyl Alcohol
50% Glycol Ether*

Slow:

Add Propylene Glycol to normal blend above.

*PM recommended

FDA Acceptability:** All components used in No-Tox inks are sanctioned by the FDA and USDA as acceptable for direct food contact.

**Note: FDA acceptability is based on the ink as supplied. Therefore no materials should be added other than those indicated in this bulletin unless specifically recommended by Colorcon.



For more information, contact your Colorcon representative or call 1-800-724-0624
You can also visit our website at <http://www.colorcon.com/notox>

©BPSI Holdings LLC, 2014

The information contained in this document is proprietary to Colorcon Inc. and may not be used or disseminated inappropriately.

All trademarks, except where noted, are property of BPSI Holdings, LLC.

The information contained herein, to the best of Colorcon Inc.'s knowledge, is true and accurate. Any recommendations or suggestions of Colorcon Inc. with regard to the products provided by Colorcon Inc. are made without warranty, either implied or expressed, because of the variations in methods, conditions and equipment which may be used in commercially processing the products, and no such warranties are made for the suitability of the products for any applications that you may have disclosed. Colorcon Inc. shall not be liable for loss of profit or for incidental, special or consequential loss or damages. The information contained in this document is not intended as legal advice, and should not be relied upon for that purpose. Any regulatory information provided is intended solely as initial general guidance. Each customer is responsible for determining the regulatory acceptability of the use of the product in their specific application.