


# ETHOCEL™ Premium Ethylcellulose Polymers Quality by Design (QbD) Case Study

Technical Bulletin




Objective: study the influence of viscosity variation of ETHOCEL (ethylcellulose) on drug release from acetaminophen (sparingly soluble) and metoprolol tartrate (freely soluble) multiparticulate dosage forms

## Multiparticulate Dosage Development



## SEM Images of ETHOCEL Coated Multiparticulate



### Critical Attributes for ETHOCEL Coating

#### Formulation & Process Attributes

##### Formulation Attributes

- ETHOCEL viscosity grade
- Solvent selection
- Water as a co-solvent (elimination of static charge)
- Plasticizer level and type
- Coating solids %
- Type and level of pore-former

##### Process Attributes

- Dew point control
- Atomization pressure and spray rate
- Product temperature

### Experimental Methods - Case Study



Extended Release Coating Parameters	Value
Solvent	Isopropyl alcohol : Water (90:10)
Solution Viscosity (cP)	70-85 cP
% Solids (w/w)	3% - 10% (7% solids for 10cP sample)
Current Ethocel Grade	10, 20, 100cP
Plasticizer	10% w/w (Dibutyl sebacate)
Weight Gain samples	2.5% to 15% WG

## Application of ETHOCEL to Model Multiparticulate Dosage (ETHOCEL 10 cP, Viscosity Specification 9-11 cP)



### Processing Conditions: Bottom Spray Würster Coating (750g)

Process Parameter	Fluidizing Airflow (m <sup>3</sup> /hr)	Inlet Air Temp (°C)	Product Temp (°C)	Outlet Temp (°C)	Spray Rate (g/minute)	Atomizing Pressure (bar)
Value	45-50	38-40	30-31	28-30	5-7	1.3

### Springly Soluble (Acetaminophen) Drug Release with ETHOCEL QbD Samples



### Freely Soluble (Metoprolol Tartrate) Drug Release with ETHOCEL QbD Samples



### Summary

- $f_2$  values were between 50 and 100 indicating that profiles can be considered similar within the viscosity specification for both sparingly and freely soluble drugs (acetaminophen and metoprolol tartrate)
- Data package available for ETHOCEL QbD samples: 7cP, 10 cP, 20 cP and 100 cP viscosity grades
- ETHOCEL QbD samples available to evaluate the effect of viscosity on drug release



For more information, contact your Colorcon representative or call:

North America +1-215-699-7733 Europe/Middle East/Africa +44-(0)-1322-293000 Asia Pacific +65-6438-0318 Latin America +54-11-5556-7700

You can also visit our website at [www.colorcon.com](http://www.colorcon.com)

©BPSI Holdings LLC, 2013. The information contained in this document is proprietary to Colorcon and may not be used or disseminated inappropriately.

All trademarks, except where noted, are property of BPSI Holdings LLC.

ETHOCEL™ is a trademark of International Flavors and Fragrances Inc. or its affiliates. © 2021 IFF. All rights reserved

TB\_ETH\_QbD\_v2\_0919